

RYMAR, LLC DATE: 01/03/10

6620 NORTH CTH J PHONE: (920) 732-3909

CATO, WI 54230 E-MAIL: rymar@rymarindustries.com

TRADE NAME MFG. PRODUCT NO.

PREMIUM CEDARTONE 85085

WEIGHT PER GALLON 7.61 POUNDS

(density)

BY WEIGHT BY VOLUME

PERCENT SOLIDS 41.54 37.63

PERCENT WATER

PERCENT SOLVENT 58.46 62.37

% EXEMPT SOLVENT

VOC (WITH WATER AND EXEMPT SOLV) 4.45 LBS/GAL 533.28 GMS/LITER

VOC (LESS WATER AND EXEMPT SOLV) 4.45 LBS/GAL 533.28 GMS/LITER

PERCENT HAPS BY WEIGHT
1.42
VOC LBS PER GALLON SOLIDS
11.83
VOC KILOGRMS PER KILOGRMS SOLIDS
1.41
VOC HAPS LBS PER GALLON SOLIDS
29
VOC HAPS LBS PER LBS SOLIDS
.03

FLASHPOINT (FAHRENHEIT) 101 F

APPLICATION BRUSH

REDUCTION NONE

CURE OVERNIGHT AIR DRY

SUBSTRATE TREATED PINE & CEDAR

COVERAGE 200-400 SQUARE FEET

VISC @ 80 F 16-18/2 ZAHN CUP